

**Best - Business, a.s.**

Havlíčková 7, 682 01 Vyškov, provozovna 679 72 Kunštát na Moravě  
tel.:+420-516/462165-9, fax: +420-516/462465, E-mail: bestb@bestb.cz

**PŘEVODNÍ TABULKA**

		<b>ZRNITOST</b>			
(etalon keramika) OZNAČENÍ	(etalon sklo) OZNAČENÍ	F 8 - 36	F 40 - 240	F 280 - 600	kN/mm <sup>2</sup>
V	Ts				92,5-97
U	Ss	1,05 - 1,20	1,15 - 1,28	1,26 - 1,35	88-92,5
T	Rs	1,20 - 1,40	1,28 - 1,45	1,35 - 1,46	83,5-88
S	Qs	1,40 - 1,64	1,45 - 1,65	1,46 - 1,60	79-83,5
R	Ps	1,64 - 1,90	1,65 - 1,90	1,60 - 1,75	74,5-79
Q	Os	1,90 - 2,20	1,90 - 2,20	1,75 - 1,95	70-74,5
P	Ns	2,20 - 2,55	2,20 - 2,55	1,95 - 2,22	65,5-70
O	Ms	2,55 - 2,90	2,55 - 2,90	2,22 - 2,50	61-65,5
N	Ls	2,90 - 3,25	2,90 - 3,25	2,50 - 2,85	56,5-61
M	Ks	3,25 - 3,65	3,25 - 3,65	2,85 - 3,22	52-56,5
L	Js	3,65 - 4,05	3,65 - 4,08	3,22 - 3,64	47,5-52
K	Is	4,05 - 4,42	4,08 - 4,55	3,64 - 4,10	43-47,5
J	Hs	4,42 - 4,85	4,55 - 5,02	4,10 - 4,60	38,5-43
I	Gs	4,85 - 5,50	5,02 - 5,60	4,60 - 5,20	34-38,5
H	Fs	5,50 - 6,20	5,60 - 6,30	5,20 - 6,00	29,5-34
G	Es	6,20 - 6,90	6,30 - 7,00	6,00 - 6,80	25-29,5
F	Ds	6,90 -	7,00 -	6,80 -	20,5-25
E	Cs				16-20,5
D	Bs				11,5-16